



POLYJET: TANGOPLUS, TANGOBLOCK, TANGOGRAY

FLEXIBLE, RUBBER-LIKE, TOUGH, EXCEPTIONAL ELONGATION

DESCRIPTIONS:

TANGOPLUS:

EXPANDS THE TANGO FAMILY OF RUBBER-LIKE MATERIALS OFFERING EXCEPTIONAL ELONGATION AT BREAK, EXCELLENT TOUGHNESS AND DURABILITY AND HIGH RESISTANCE TO TEARING. IT ADDRESSES A BROAD RANGE OF APPLICATIONS REQUIRING RUBBER - LIKE FLEXIBILITY AND DURABILITY, SUCH AS GASKETS AND SEALS, HOSES, ATHLETIC FOOTWEAR, TOYS AND MORE.

TANGOBLOCK AND TANGOGRAY:

TANGOBLOCK AND TANGOGRAY RUBBER LIKE FLEXIBLE 3D MODELING MATERIALS ENABLES MODELS THAT CLOSELY RESEMBLE THAT "FEEL" OF FLEXIBLE TARGET PRODUCTS. TANGOBLOCK AND TANGOGRAY ENABLE A REALISTIC RUBBER/SILICONE FEEL, AND EASILY STRETCH TO FIT ONTO OTHER PARTS. THEY ARE PARTICULARLY IDEAL FOR MANY CONSUMER ELECTRONICS APPLICATIONS, SHOES, TOYS, GENERAL INDUSTRIAL APPLICATIONS, AND RAPID TOOLING.

APPLICATIONS:

- RUBBER-LIKE MATERIAL ENABLES 3-D PARTS TO BE USED IN THE EARLY DESIGN STAGES, SHORTENING THE PRODUCT DESIGN CYCLE
- VERY HIGH ELONGATION AT BREAK, SPECIFICALLY FOR TANGOPLUS, PROVIDES A REALISTIC FEEL OF RUBBER AND SILICONE AND ENABLES MODEL PARTS THAT STRETCH EASILY TO FIT WITH OTHER PARTS.
- CHOICE OF FLEXIBILITY AND HARDNESS LEVELS- TANGOBLOCK (ELONGATION AT BREAK OF 47.7% AND 61 SHORE SCALE A); TANGOGRAY (ELONGATION AT BREAK OF 47% AND 75 SHORE SCALE A); TANGOPLUS (ELONGATION AT BREAK OF 218% AND 27 SHORE SCALE A).

FULLCURE® 900

PROPERTY	ASTM	METRIC UNITS	TANGOPLUS	TANGOGRAY	TANGOBLOCK
TENSILE STRENGTH	D638M	MPA	N/A	4.36	2
ELONGATION AT BREAK	D638M	%	218	47	47.7
COMPRESSIVE SET	D395	%	4.4	1	0.8
HARDNESS (SHORE D)	D2240		27 SCALE D	75 SCALE A	61 SCALE A
TENSILE TEAR RESISTANCE	D624	KG/CM	3.47	9.5	3.8

3020 RED HILL AVENUE
COSTA MESA, CA 92626
PHONE 888.496.3406
FAX 714.641.3111

DINSMOREINC.COM



SERVICES AVAILABLE

PRODUCT DESIGN
RAPID PROTOTYPING
SLA
FRSLA
POLYJET
SLS
DMLS
FDM
PLASTIC CASTING
CNC MACHINING
INJECTION MOLD TOOLING
RAPID TOOLING
PRODUCTION TOOLING
INJECTION MOLDING
METAL CASTING